252FP6212-02 06/2019





## **ENGLISH PRECAUTIONS**

## Dry milling is recommended.

If wet milling/grinding is performed by using cooling water contaminated by silica-based glass ceramics(lithium disilicate glass,etc.), the translucency of the zirconia may be reduced after baking. Before wet milling/grinding, clean the milling/grinding chamber, cooling water tank and filter insert. The cooling water must be changed in order to assure optimum results.

## Kuraray Noritake Dental Inc.

300 Higashiyama, Miyoshi-cho, Miyoshi, Aichi 470-0293, Japan TFL +81-561-32-8953 FAX +81-561-32-8976 **( (** 1639 [

Philipp-Reis-Str. 4.

65795 Hattersheim am Main, Germany

US Distributed by

Kuraray America, Inc. 32 Old Slip,7th Floor, New York, NY 10005